

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 April 2002 (18.04.2002)

PCT

(10) International Publication Number
WO 02/30998 A1

(51) International Patent Classification⁷: **C08F 4/651**,
4/654, 10/00

(21) International Application Number: **PCT/EP01/11048**

(22) International Filing Date:
24 September 2001 (24.09.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00203535.0 13 October 2000 (13.10.2000) EP

(71) Applicant (for all designated States except US): **BASELL
TECHNOLOGY COMPANY B.V.** [NL/NL]; Hoeksteen
66, NL-2132 MS Hoofddorp (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MORINI, Gi-
ampiero** [IT/IT]; Via Giotto 36, I-35100 Padova (IT).
BALBONTIN, Giulio [IT/IT]; Via Goretti 111, I-44100
Ferrara (IT).

(74) Agents: **COLUCCI, Giuseppe**; Basell Poliolefine Italia
S.p.A., Intellectual Property, P.le G. Donegani, 12, I-44100
Ferrara et al. (IT).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK,
SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA,
ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD,
TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report
— before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

WO 02/30998 A1

(54) Title: CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS

(57) Abstract: The present invention relates to catalyst components for the polymerization of olefins comprising Mg, Ti, halogen and at least two electron donor compounds, said catalyst component being characterized by the fact that at least one of the electron donor compounds, present in an amount from 20 to 50% by mol with respect to the total amount of donors, is selected from esters of succinic acids which are not extractable, for more than 25% by mol and at least another electron donor compound which is extractable, for more than 35%. The said catalyst component are capable to give polymers with high xylene insolubility, high stereoblock content and broad MWD suitable for making the polymers usable in the BOPP sector.

CATALYST COMPONENTS FOR THE POLYMERIZATION OF OLEFINS

The present invention relates to catalyst components for the polymerization of olefins, in particular propylene, comprising a Mg dihalide based support on which are deposited a Ti compound having at least one Ti-halogen bond and at least two electron donor compounds selected from specific classes. The present invention further relates to the catalysts obtained from said components and to their use in processes for the polymerization of olefins. The catalysts of the present invention are able to give, with high yields, propylene homopolymers characterized by high xylene insolubility, a broad range of isotacticity and, in particular conditions by a very high content of stereoblocks.

Catalyst components for the stereospecific polymerization of olefins are widely known in the art. The most largely widespread family of catalyst systems comprises a solid catalyst component, constituted by a magnesium dihalide on which are supported a titanium compound and an internal electron donor compound, used in combination with an Al-alkyl compound. Conventionally however, when a higher crystallinity of the polymer is required, also an external donor (for example an alkylalkoxysilane) is needed in order to obtain higher isotacticity. One of the preferred classes of internal donors is constituted by the esters of phthalic acid, diisobutylphthalate being the most used. This catalyst system is capable to give very good performances in terms of activity, isotacticity and xylene insolubility provided that an external electron donor compound is used. When the external donor is missing, low yields, low xylene insolubility and poor isotacticity are obtained. On the other hand, when the external donor is used, high xylene insolubility is obtained only together with a high isotacticity. Moreover, the Molecular Weight Distribution (MWD) is, under the normal single step polymerization conditions, not broad (Polydispersity Index in the range 3.6-4.5). These characteristics, although useful in certain applications, are not desirable in certain other fields such as the production of bi-oriented polypropylene films (BOPP). For application in this field in fact, polypropylenes are required to have a broad MWD (Polydispersity Index higher than 5) a lower flexural modulus (obtainable by lowering crystallinity of the polymer) while at the same time retaining a high xylene insolubility. Moreover, it has been found that suitable polymers for application in this field are those that, in addition to the above requirements, have also a comparatively high content of the so called stereoblocks, i.e., of polymer fractions which, although predominantly isotactic, contain a not negligible amount of non-isotactic sequences of propylene units. In the

conventional fractionation techniques such as the TREF (Temperature Rising Elution Temperature) those fractions are eluted at temperatures lower than those are necessary for the more isotactic fractions. In EP 658577 is described a method for producing PP homopolymers having a high stereoblock content. It comprises polymerizing propylene in the presence of a catalyst comprising (i) a solid catalyst component in which a Ti compound and diisobutyl phthalate are supported on a $MgCl_2$, (ii) an Al-alkyl compound as a co-catalyst and (iii) a 3,3,3-trifluoropropyl(alkyl)dimethoxysilane as external donor. In example 1 it can be seen that although the polymerization is carried out in two sequential steps under different conditions, the MWD of the bimodal polymer obtained is not sufficiently broad (Polydispersity Index 4.7). Furthermore, the bimodal polymers can have problems of homogeneity due to presence of distinct fractions with pronounced difference in average Mw. In said example 1 the weight percentage of stereoblock fraction measured via TREF, on the polymer after visbreaking, is about 31%, while in another run (in Table 2) the amount of stereoblock fraction was about 26%. In view of the above, it would be desirable to have a catalyst component with still improved characteristics and in particular capable to give polymers with high xylene insolubility, high stereoblock content and broad MWD suitable for making the polymers usable in the BOPP sector.

It has now unexpectedly been found a catalyst component having the above advantages which comprises Mg, Ti, halogen and two electron donor compounds selected from specific classes.


It is therefore an object of the present invention a catalyst component for the polymerization of olefins $CH_2=CHR$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising Mg, Ti, halogen and at least two electron donor compounds, said catalyst component being characterized by the fact that at least one of the electron donor compounds, which is present in an amount from 15 to 50% by mol with respect to the total amount of donors, is selected from esters of succinic acids which are not extractable, under the conditions described below, for more than 20% by mol and at least another electron donor compound which is extractable, under the same conditions, for more than 30% by mol.

According to the present invention, the esters of succinic acids not extractable for more than 20% by mol will be defined as non-extractable succinates. The electron donor compounds extractable for more than 30% by mol will be defined as extractable electron donor compounds. Preferably, the amount of non-extractable succinates is between 20 and 45 and more preferably

from 22 to 40% by mol with respect to the total amount of the electron donor compounds.

In a preferred embodiment is used a succinate which is not extractable for more than 15% and another electron donor compound which is extractable for more than 35%.

Among the non-extractable succinates mentioned above, particularly preferred are the succinates of formula (I) below



in which the radicals R_1 and R_2 , equal to, or different from, each other are a C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms; and the radicals R_3 and R_4 equal to, or different from, each other, are C_1 - C_{20} alkyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms with the proviso that at least one of them is a branched alkyl; said compounds being, with respect to the two asymmetric carbon atoms identified in the structure of formula (I), stereoisomers of the type (S,R) or (R,S) that are present in pure forms or in mixtures.


R_1 and R_2 are preferably C_1 - C_8 alkyl, cycloalkyl, aryl, arylalkyl and alkylaryl groups. Particularly preferred are the compounds in which R_1 and R_2 are selected from primary alkyls and in particular branched primary alkyls. Examples of suitable R_1 and R_2 groups are methyl, ethyl, n-propyl, n-butyl, isobutyl, neopentyl, 2-ethylhexyl. Particularly preferred are ethyl, isobutyl, and neopentyl.

Particularly preferred are the compounds in which the R_3 and/or R_4 radicals are secondary alkyls like isopropyl, sec-butyl, 2-pentyl, 3-pentyl or cycloalkyls like cyclohexyl, cyclopentyl, cyclohexylmethyl.

Examples of the above-mentioned compounds are the (S,R) (S,R) forms pure or in mixture, optionally in racemic form, of diethyl 2,3-bis(trimethylsilyl)succinate, diethyl 2,3-bis(2-ethylbutyl)succinate, diethyl 2,3-dibenzylsuccinate, diethyl 2,3-diisopropylsuccinate, diisobutyl 2,3-diisopropylsuccinate, diethyl 2,3-bis(cyclohexylmethyl)succinate, diethyl 2,3-

diisobutylsuccinate, diethyl 2,3-dineopentylsuccinate, diethyl 2,3-dicyclopentylsuccinate, diethyl 2,3-dicyclohexylsuccinate.

Among the extractable electron donor compounds particularly preferred are the esters of mono or dicarboxylic organic acids such as benzoates, malonates, phthalates and succinates. Among malonates particularly preferred are those of formula (II):




where R_1 is H or a $\text{C}_1\text{-C}_{20}$ linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, R_2 is a $\text{C}_1\text{-C}_{20}$ linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, R_3 and R_4 , equal to, or different from, each other, are $\text{C}_1\text{-C}_{20}$ linear or branched alkyl groups or $\text{C}_3\text{-C}_{20}$ cycloalkyl groups.

Preferably, R_3 and R_4 are primary, linear or branched $\text{C}_1\text{-C}_{20}$ alkyl groups, more preferably they are primary branched $\text{C}_4\text{-C}_{20}$ alkyl groups such as isobutyl or neopentyl groups.

R_2 is preferably, in particular when R_1 is H, a linear or branched $\text{C}_3\text{-C}_{20}$ alkyl, cycloalkyl, or arylalkyl group; more preferably R_2 is a $\text{C}_3\text{-C}_{20}$ secondary alkyl, cycloalkyl, or arylalkyl group.

Preferred esters of aromatic carboxylic acids are selected from $\text{C}_1\text{-C}_{20}$ alkyl or aryl esters of benzoic and phthalic acids, possibly substituted. The alkyl esters of the said acids being preferred. Particularly preferred are the $\text{C}_1\text{-C}_6$ linear or branched alkyl esters. Specific examples are ethylbenzoate, n-butylbenzoate, p-methoxy ethylbenzoate, p-ethoxy ethylbenzoate, isobutylbenzoate, ethyl p-toluate, diethyl phthalate, di-n-propyl phthalate, di-n-butyl phthalate, di-n-pentyl phthalate, di-i-pentyl phthalate, bis(2-ethylhexyl) phthalate, ethyl-isobutyl phthalate, ethyl-n-butyl phthalate, di-n-hexyl phthalate, di-isobutylphthalate.

Among succinates there are many subclasses of compounds that can be used as extractable donors according to the present invention. One of the preferred groups of compounds is that described by the formula (III)



in which R_3 to R_5 are hydrogen and R_6 is a branched alkyl, cycloalkyl, aryl, arylalkyl and alkylaryl radical having from 3 to 10 carbon atoms. Particularly preferred are the compounds in which R_6 is a branched primary alkyl group or a cycloalkyl group having from 3 to 10 carbon atoms. Specific examples are diethyl sec-butylsuccinate, diethyl hexylsuccinate, diethyl cyclopropylsuccinate, diethyl norbornylsuccinate, diethyl (10-)perhydronaphthylsuccinate, diethyl trimethylsilylsuccinate, diethyl methoxysuccinate, diethyl p-methoxyphenylsuccinate, diethyl p-chlorophenylsuccinate diethyl phenylsuccinate, diethyl cyclohexylsuccinate, diethyl benzylsuccinate, diethyl (cyclohexylmethyl)succinate, diethyl t-butylsuccinate, diethyl isobutylsuccinate, diethyl isopropylsuccinate, diethyl neopentylsuccinate,

Another subclass of preferred compounds is that of formula (III) in which R_3 and R_4 are hydrogen and R_5 and R_6 are selected from C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms. Specific examples of suitable 2,2-disubstituted succinates are: diethyl 2,2-dimethylsuccinate, diethyl 2-ethyl-2-methylsuccinate, diethyl 2-benzyl-2-isopropylsuccinate, diethyl 2-(cyclohexylmethyl)-2-isobutylsuccinate, diethyl 2-cyclopentyl-2-n-propylsuccinate, diethyl 2,2-diisobutylsuccinate, diethyl 2-cyclohexyl-2-ethylsuccinate, diethyl 2-isopropyl-2-methylsuccinate, diethyl 2,2-diisopropyl diethyl 2-isobutyl-2-ethylsuccinate, diethyl 2-(1,1,1-trifluoro-2-propyl)-2-methylsuccinate, diethyl 2-isopentyl-2-isobutylsuccinate, diethyl 2-phenyl-2-n-butylsuccinate, diisobutyl 2,2-dimethylsuccinate, diisobutyl 2-ethyl-2-methylsuccinate, diisobutyl 2-benzyl-2-isopropylsuccinate, diisobutyl 2-(cyclohexylmethyl)-2-isobutylsuccinate, diisobutyl 2-cyclopentyl-2-n-propylsuccinate.

Moreover, also preferred are the (*S,S*), (*R,R*) or *meso* forms of the succinates of formula (I) described above.

Mixtures of different succinates of formula (I) can be used as non-extractable donors, and

mixtures of extractable donors can be used as well. In particular, we found it particularly advantageous the use of the succinates of formula (I) in which R_3 and R_4 are identical both as extractable and non extractable electron donors. Actually, the compounds of formula (I) in which R_3 and R_4 are the same are often mixtures of meso (S,S and R,R) and rac- form (S,R and R,S) as a direct result of their preparation process. Therefore, in certain cases the skilled in the art is already provided with a mixture of extractable and non-extractable donors to be used in the preparation of the catalyst of the invention. Depending on the peculiar amounts of the single donors in the mixtures, additional amounts of extractable donors could be requested in order to bring the final composition of the catalyst within the limits set forth above .

It has been found particularly interesting the use of a catalyst component comprising the *rac*-form of diethyl or diisobutyl 2,3-diisopropylsuccinate as non-extractable donor and the *meso* form of diethyl or diisobutyl 2,3-diisopropylsuccinate together with an alkylphthalate as extractable donors.

As explained above, the catalyst components of the invention comprise, in addition to the above electron donors, Ti, Mg and halogen. In particular, the catalyst components comprise a titanium compound, having at least a Ti-halogen bond and the above mentioned electron donor compounds supported on a Mg halide. The magnesium halide is preferably $MgCl_2$ in active form which is widely known from the patent literature as a support for Ziegler-Natta catalysts. Patents USP 4,298,718 and USP 4,495,338 were the first to describe the use of these compounds in Ziegler-Natta catalysis. It is known from these patents that the magnesium dihalides in active form used as support or co-support in components of catalysts for the polymerization of olefins are characterized by X-ray spectra in which the most intense diffraction line that appears in the spectrum of the non-active halide is diminished in intensity and is replaced by a halo whose maximum intensity is displaced towards lower angles relative to that of the more intense line.

The preferred titanium compounds used in the catalyst component of the present invention are $TiCl_4$ and $TiCl_3$; furthermore, also Ti-haloalcoholates of formula $Ti(OR)_{n-y}X_y$ can be used, where n is the valence of titanium, y is a number between 1 and $n-1$ X is halogen and R is a hydrocarbon radical having from 1 to 10 carbon atoms.

The preparation of the solid catalyst component can be carried out according to several methods. According to one of these methods, the magnesium dichloride in an anhydrous state, the titanium compound and the electron donor compounds are milled together under conditions in

which activation of the magnesium dichloride occurs. The so obtained product can be treated one or more times with an excess of TiCl_4 at a temperature between 80 and 135°C. This treatment is followed by washings with hydrocarbon solvents until chloride ions disappeared. According to a further method, the product obtained by co-milling the magnesium chloride in an anhydrous state, the titanium compound and the electron donor compounds are treated with halogenated hydrocarbons such as 1,2-dichloroethane, chlorobenzene, dichloromethane etc. The treatment is carried out for a time between 1 and 4 hours and at temperature of from 40°C to the boiling point of the halogenated hydrocarbon. The product obtained is then generally washed with inert hydrocarbon solvents such as hexane.

According to another method, magnesium dichloride is preactivated according to well known methods and then treated with an excess of TiCl_4 at a temperature of about 80 to 135°C in the presence of the electron donor compounds. The treatment with TiCl_4 is repeated and the solid is washed with hexane in order to eliminate any non-reacted TiCl_4 .

A further method comprises the reaction between magnesium alcoholates or chloroalcoholates (in particular chloroalcoholates prepared according to USP 4,220,554) and an excess of TiCl_4 in the presence of the electron donor compounds at a temperature of about 80 to 120°C.

According to a preferred method, the solid catalyst component can be prepared by reacting a titanium compound of formula $\text{Ti}(\text{OR})_{n-y}\text{X}_y$, where n is the valence of titanium and y is a number between 1 and n, preferably TiCl_4 , with a magnesium chloride deriving from an adduct of formula MgCl_2pROH , where p is a number between 0.1 and 6, preferably from 2 to 3.5, and R is a hydrocarbon radical having 1-18 carbon atoms. The adduct can be suitably prepared in spherical form by mixing alcohol and magnesium chloride in the presence of an inert hydrocarbon immiscible with the adduct, operating under stirring conditions at the melting temperature of the adduct (100-130°C). Then, the emulsion is quickly quenched, thereby causing the solidification of the adduct in form of spherical particles. Examples of spherical adducts prepared according to this procedure are described in USP 4,399,054 and USP 4,469,648. The so obtained adduct can be directly reacted with Ti compound or it can be previously subjected to thermal controlled dealcoholation (80-130°C) so as to obtain an adduct in which the number of moles of alcohol is generally lower than 3 preferably between 0.1 and 2.5. The reaction with the Ti compound can be carried out by suspending the adduct (dealcoholated or as such) in cold TiCl_4 (generally 0°C); the mixture is heated up to 80-130°C and kept at this temperature for 0.5-

2 hours. The treatment with TiCl_4 can be carried out one or more times. The electron donor compounds can be added during the treatment with TiCl_4 . They can be added together in the same treatment with TiCl_4 or separately in two or more treatments.

The preparation of catalyst components in spherical form is described for example in European Patent Applications EP-A-395083, EP-A-553805, EP-A-553806, EPA-601525 and WO98/44009.

The solid catalyst components obtained according to the above method show a surface area (by B.E.T. method) generally between 20 and 500 m^2/g and preferably between 50 and 400 m^2/g , and a total porosity (by B.E.T. method) higher than 0.2 cm^3/g preferably between 0.2 and 0.6 cm^3/g . The porosity (Hg method) due to pores with radius up to 10000 Å generally ranges from 0.3 to 1.5 cm^3/g , preferably from 0.45 to 1 cm^3/g .

A further method to prepare the solid catalyst component of the invention comprises halogenating magnesium dihydrocarbyloxy compounds, such as magnesium dialkoxide or diaryloxy, with solution of TiCl_4 in aromatic hydrocarbon (such as toluene, xylene etc.) at temperatures between 80 and 130°C. The treatment with TiCl_4 in aromatic hydrocarbon solution can be repeated one or more times, and the electron donor compounds are added during one or more of these treatments.

In any of these preparation methods the desired electron donor compounds and in particular those selected from esters of carboxylic acids, can be added as such or, in an alternative way, it can be obtained *in situ* by using an appropriate precursor capable to be transformed in the desired electron donor compound by means, for example, of known chemical reactions such as esterification, transesterification, etc.

Regardless to the preparation method used, the final amount of the two or more electron donor compounds is such that the molar ratio with respect to the MgCl_2 is from 0.01 to 1, preferably from 0.05 to 0.5.

The solid catalyst components according to the present invention are converted into catalysts for the polymerization of olefins by reacting them with organoaluminum compounds according to known methods.

In particular, it is an object of the present invention a catalyst for the polymerization of olefins $\text{CH}_2=\text{CHR}$, in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising the product of the reaction between:

- (i) the solid catalyst component as disclosed above,
- (ii) an organo-metal compound and
- (iii) an external electron donor compound.

The organo-metal compound (ii) is preferably chosen among alkyl-Al compounds and in particular among the trialkyl aluminum compounds such as for example triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum. It is also possible to use alkylaluminum halides, alkylaluminum hydrides or alkylaluminum sesquichlorides, such as AlEt_2Cl and $\text{Al}_2\text{Et}_3\text{Cl}_3$, possibly in mixture with the above cited trialkylaluminums.

Suitable external electron-donor (iii) include silanes, ethers, esters, amines, heterocyclic compounds and ketones. A particular class of preferred external donor compounds is that of silanes of formula $\text{R}_a^5\text{R}_b^6\text{Si}(\text{OR}^7)_c$, where a and b are integers from 0 to 2, c is an integer from 1 to 4 and the sum (a+b+c) is 4; R^5 , R^6 , and R^7 , are alkyl, alkylen, cycloalkyl or aryl radicals with 1-18 carbon atoms optionally containing heteroatoms. Particularly preferred are the silicon compounds in which a is 1, b is 1, c is 2, at least one of R^5 and R^6 is selected from branched alkyl, cycloalkyl or aryl groups with 3-10 carbon atoms optionally containing heteroatoms and R^7 is a C_1 - C_{10} alkyl group, in particular methyl. Examples of such preferred silicon compounds are methylcyclohexyldimethoxysilane, dicyclopentyldimethoxysilane.

Although the above disclosed catalyst are able to give propylene polymers with high xylene insolubility, high stereoblock content and broad MWD it has been found that polymers with particularly increased stereoblock content and broad MWD are obtainable using as external donors certain silanes of the above disclosed formula having a relatively low stereoregulating ability. By the term "low stereoregulating ability" we mean silanes that under the standard polymerization conditions described below give propylene polymers with a content of pentads (mmmm) equal to or lower than 97%. The skilled in the art can easily determine the stereoregulating ability of the relevant silanes by performing the polymerization test under the conditions described below. In addition, the applicant found that a group of silanes with a low stereoregulating ability are those of the formula disclosed above in which R^5 is methyl, R^6 is a C_1 - C_{15} linear alkyl and R^7 is a linear C_1 - C_4 alkyl. Preferred examples of these silanes are n-propyl-methyl-dimethoxysilane; n-butyl-methyl-dimethoxysilane; n-pentyl-methyl-dimethoxysilane; n-hexyl-methyl-dimethoxysilane; n-octyl-methyl-dimethoxysilane; n-decyl-

methyl- dimethoxysilane. A further group of silanes with low stereoregulating ability is that of the formula above described in which c is 3 or 4. Particularly preferred are the alkyltrialkoxysilanes and the tetraalkoxysilanes in which R^7 is a linear C1-C8 alkyl.

Another group of silanes with a low stereoregulating ability are those of the formula disclosed above in which R^5 is a trifluoropropyl group, optionally substituted, R^6 is a C1-C6 linear alkyl or a piperidinyl group, optionally substituted, and R^7 is a linear C1-C4 alkyl. Preferred examples of these silanes are (3,3,3-trifluoro-*n*-propyl)(2-ethylpiperidinyl)dimethoxysilane, methyl(3,3,3-trifluoro-*n*-propyl)dimethoxysilane.

The electron donor compound (iii) is used in such an amount to give a molar ratio between the organoaluminum compound and said electron donor compound (iii) of from 0.1 to 500, preferably from 1 to 300 and more preferably from 3 to 100.

The polymerization process can be carried out according to known techniques for example slurry polymerization using as diluent an inert hydrocarbon solvent, or bulk polymerization using the liquid monomer (for example propylene) as a reaction medium. Moreover, it is possible to carry out the polymerization process in gas-phase operating in one or more fluidized or mechanically agitated bed reactors.

The polymerization is generally carried out at temperature of from 20 to 120°C, preferably of from 40 to 80°C. When the polymerization is carried out in gas-phase the operating pressure is generally between 0.5 and 5 MPa, preferably between 1 and 4 MPa. In the bulk polymerization the operating pressure is generally between 1 and 8 MPa preferably between 1.5 and 5 MPa.

As explained above, the catalysts of the invention when used in the polymerization of propylene are able to give polymers with a range of isotacticity (expressed in term of percentage of mmmm pentads), MWD and stereoblock content such that they are particularly suitable for use in the BOPP field. It is particular worth noting that the high values of P.I. are obtained in a single polymerization step i.e., with a substantially monomodal distribution which allow to avoid any problem due to non homogeneity of the product.

Therefore, it constitutes a further object of the present invention a propylene polymer having the following characteristics:

a stereoblock content of 18% or higher measured by the TREF method described below;

a Polydispersity Index of at least 5 and

a percentage of pentads (mmmm), measured by NMR, lower than or equal to 97.

Preferably the stereoblock content is higher than 20 and more preferably higher than 22. The P.I. is preferably higher than 5.3 and the percentage of pentads is preferably lower than 96.5 and more preferably lower than 95.5. It has moreover been found that particularly interesting polypropylenes are those disclosed above and further characterized by a showing, at the TREF analysis, a fraction eluted at a temperature ranging from 110° and 114°C which accounts for more than 25% of the total weight of the polymer. Preferably it accounts for more than 33%. Also preferred are the polypropylenes with a TREF profile such that the fraction eluted at a temperature between 115° and 120°C accounts for a value between 0.1 and 10%, preferably between 0.5 and 5%, of the total weight of the polymer.

CHARACTERIZATIONS

Test for the extractability of the electron donor (ED) compounds

A. Preparation of the solid catalyst component

Into a 500ml four-necked round flask, purged with nitrogen, 250 ml of TiCl_4 were introduced at 0°C. While stirring, 10.0 g of microspheroidal $\text{MgCl}_2 \cdot 2.8\text{C}_2\text{H}_5\text{OH}$ (prepared according to the method described in ex.2 of USP 4,399,054 but operating at 3,000 rpm instead of 10,000) were introduced. 4.4 mMols of the selected electron donor compound were also added.

The temperature was raised to 100 °C and maintained at that temperature for 120 min. Then, the stirring was discontinued, the solid product was allowed to settle and the supernatant liquid was siphoned off.

250 ml of fresh TiCl_4 were added. The mixture was reacted at 120°C for 60 min under stirring and, then, the supernatant liquid was siphoned off. The solid (A) was washed six times with anhydrous hexane (6 x 100 ml) at 60 °C, dried under vacuum and analyzed for the quantitative determination of Mg and electron donor compound. The type of electron donor compound and its molar ratio with respect to Mg (ratio A) are reported in Table 1.

B. Treatment of solid A

In a 250 ml jacketed glass reactor with mechanical stirrer and filtration septum are introduced under nitrogen atmosphere 190 ml of anhydrous n-hexane, 19 mMmoles of AlEt_3 and 2 gr of the catalyst component prepared as described in A. The mixture is heated at 60°C for 1 hour under stirring (stirring speed at 400 rpm). After that time the mixture is filtered, washed four times with n-hexane at 60°C and finally dried under vacuum for 4 hours at 30°C. The solid is then analyzed for the quantitative determination of Mg and electron donor compound. The type of

electron donor compound and its molar ratio with respect to Mg (ratio B) are reported in Table 1. The extractability of the electron donor compound is calculated according to the following formula: %of ED extracted = (Ratio A-Ratio B)/Ratio A

Polymer microstructure analysis

50 mg of each xylene insoluble fraction were dissolved in 0.5 ml of C₂D₂Cl₄.

The ¹³C NMR spectra were acquired on a Bruker DPX-400 (100.61 Mhz, 90° pulse, 12s delay between pulses). About 3000 transients were stored for each spectrum; mmmm pentad peak (21.8 ppm) was used as reference.

The microstructure analysis was carried out as described in literature (*Polymer*, 1984, 25, 1640, by Inoue Y. et Al. and *Polymer*, 1994, 35, 339, by Chujo R. et Al.).

Determination of X.I.

2.5g of polymer were dissolved in 250 ml of o-xylene under stirring at 135°C for 30 minutes, then the solution was cooled to 25°C and after 30 minutes the insoluble polymer was filtered. The resulting solution was evaporated in nitrogen flow and the residue was dried and weighed to determine the percentage of soluble polymer and then, by difference, the X.I. %.

TREF method

TREF fractionation of the polymer was carried out by dissolving 1 g of propylene polymer in o-xylene at 135°C and slowly cooling (20 h) to 25°C in a column loaded with glass beads. Elution with o-xylene (600 mL/h) was first carried out at 25°C for 1 h to obtain a xylene-soluble fraction. The column temperature was then raised from 25 to 95°C at a rate of 0.7°C/min without elution and the temperature was held at 95°C for 2 h before eluting at this temperature for 1 h to yield a single fraction. Finally, elution was continued while raising the temperature from 95 to 120°C at a rate of 3°C/h, collecting individual fractions at temperature intervals of 1°C. According to the present invention the stereoblock content is considered as the total weight of the fractions, insoluble in xylene at 25°C, that are eluted at a temperature lower than 100°C based on the total weight of the polymer.

Determination of polydispersity index (P.I.)

This property is strictly connected with the molecular weight distribution of the polymer under examination. In particular it is inversely proportional to the creep resistance of the polymer in the molten state. Said resistance called modulus separation at low modulus value (500 Pa), was determined at a temperature of 200 °C by using a parallel plates rheometer model

RMS-800 marketed by RHEOMETRICS (USA), operating at an oscillation frequency which increases from 0.1 rad/sec to 100 rad/sec. From the modulus separation value, one can derive the P.I. by way of the equation:

$$P.I. = 54.6 * (\text{modulus separation})^{-1.76}$$

in which the modulus separation is defined as:

$$\text{modulus separation} = \text{frequency at } G' = 500\text{Pa} / \text{frequency at } G'' = 500\text{Pa}$$

wherein G' is storage modulus and G'' is the loss modulus.

Standard Test of Polymerization for evaluation of silane stereocontrol

Preparation of the solid catalyst component

Into a 500 mL four-necked round flask, purged with nitrogen, 250 mL of TiCl_4 were introduced at 0 °C. While stirring, 10.0 g of microspheroidal $\text{MgCl}_2 \cdot 2.8\text{C}_2\text{H}_5\text{OH}$ (prepared according to the method described in ex.2 of USP 4,399,054 but operating at 3000 rpm instead of 10000 rpm) and 10.1 mMol of diisobutylphthalate are added. The temperature was raised to 100 °C and maintained for 120 min. Then, the stirring was discontinued, the solid product was allowed to settle and the supernatant liquid was siphoned off. Then 250 mL of fresh TiCl_4 were added. The mixture was reacted at 120 °C for 60 min and, then, the supernatant liquid was siphoned off. The solid was washed six times with anhydrous hexane (6 x 100 mL) at 60 °C. Finally, the solid was dried under vacuum.

In a 4 liter autoclave, purged with nitrogen flow at 70 °C for one hour, are introduced in propylene flow at 30 °C 75 mL of anhydrous hexane containing 800 mg of AlEt_3 , an amount of silane such as to provide an Al/Si ratio of 20 and 10 mg of a solid catalyst component prepared as described above. The autoclave was closed. 1.5 NL of hydrogen were added and then, under stirring, 1.2 kg of liquid propene were fed. The temperature was raised to 70 °C in five minutes and the polymerization was carried out at this temperature for two hours. The nonreacted propylene was removed, the polymer was collected, dried at 70 °C under vacuum for three hours, weighed, and subject to xylene insolubility determination. The insoluble portion is analyzed to determine the percentage of pentads (mmmm) according to the method described above.

Examples 1-4 and Comparative Examples 1-3

Preparation of solid catalyst components.

Into a 500ml four-necked round flask, purged with nitrogen, 250 ml of TiCl_4 were introduced at

0°C. While stirring, 10.0 g of microspheroidal $\text{MgCl}_2 \cdot 2.8\text{C}_2\text{H}_5\text{OH}$ (prepared according to the method described in ex.2 of USP 4,399,054 but operating at 3,000 rpm instead of 10,000) were introduced. As internal donor(s), 7.6 mMols of a previously prepared mixture of esters were also added. Type(s) of internal donors and amounts are reported in Table 2.

The temperature was raised to 100 °C and maintained for 120 min. Then, the stirring was discontinued, the solid product was allowed to settle and the supernatant liquid was siphoned off.

250 ml of fresh TiCl_4 were added. The mixture was reacted at 120°C for 60 min and, then, the supernatant liquid was siphoned off. The solid was washed six times with anhydrous hexane (6 x 100 ml) at 60 °C. Finally, the solid was dried under vacuum and analyzed. The types and amounts of esters (wt %) and the amount of Ti (wt %) contained in the solid catalyst component are reported in Table 2.

Polymerization examples 5-17 and comparative examples C4-C10

In a 4 liter autoclave, purged with nitrogen flow at 70 °C for one hour, 75 ml of anhydrous hexane containing 7 mMols of AlEt_3 , the external donor (type and amount are reported in the Table 3) and 10 mg of solid catalyst component were introduced in propylene flow at 30 °C. The autoclave was closed, 1.5 NI of hydrogen were added and then, under stirring, 1.2 Kg of liquid propylene were fed. The temperature was raised to 70°C in five minutes and the polymerization was carried out at this temperature for two hours. The unreacted propylene was vented, the polymer was recovered and dried at 70 °C under vacuum for three hours and, then, weighed and fractionated with o-xylene to determine the amount of the xylene insoluble (X.I.) fraction at 25°C and its microstructure.

Polymerization results are reported in Table 3.

Table 1

ED	ED/Mg ratio A (mMols/gram atom)	ED/Mg ratio A (mMols/gram atom)	ED extracted (mol%)
Type			
<i>rac</i> Diethyl 2,3-diisopropylsuccinate	65.2	62.8	4
<i>Meso</i> Diethyl 2,3-diisopropylsuccinate	39.3	23.9	39
Diisobutyl phthalate	48.8	8.8	82

Table 2

Preparation conditions				Composition			
Ex.	Fed in the preparation		Ti	not extractable succinate		Extractable ED	
	Not extractable succinate	Extractable ED					% of not extractable succinate on total I.D.
N°	Type	MMols	Type(s)	Wt%	MMols	Type	Wt%
1	A	0.76	B	3.3	6.84	A	2.4
2	A	1.14	B	3.8	6.46	A	3.24
3	A	1.67	B	4.2	1.37	A	3.53
			DIBP		4.56	DIBP	7.6
4	C	1.25	D	3.4	1.79	C	4.4
			DIBP		4.56	DIBP	1.46
C1	---	---	B	3.8	7.6	---	6.6
C2	A	2.8	B	3.5	4.8	A	10.7
C3	---	---	DIBP	2.5	7.6	---	7.45
						DIBP	7.1

A = *rac* Diethyl 2,3-diisopropylsuccinate
 B = *meso* Diethyl 2,3-diisopropylsuccinate
 C = *rac* Diisobutyl 2,3-diisopropylsuccinate
 D = *meso* Diisobutyl 2,3-diisopropylsuccinate
 DIBP = Diisobutylphthalate

Table 3

Polym. Example N°	Catalyst Ex. N°	Ext. Donor Type	Ext. Donor Amount Mmoles	Activity Kg/g	X.I. %	P.I	Pentads (mmmm) %	TREF	
								%wt 25-99°C	%wt 110-114°C
5	1	G	0.35	33	94.3	5.8	93.2		
6	2	G	0.35	43	95.8	5.9	94.8	20.1	34.1
7	3	G	0.35	45	97.2	5.3	95		
8	3	G	0.18	48	96.1	5.2	94.5	20.3	40.9
9	3	H	0.35	47	94.4	5.3	94.1	27.2	28.4
10	3	I	0.35	29	97	5.4	96.3		
11	3	I	0.18	36	94.5	5.6	95.2		
12	3	J	0.35	21	97.1	5.5	96.1	19.3	52.5
13	3	J	0.18	26	96.1	5.8	96.2		
14	3	K	0.35	25	96	5.5	96.5		
15	3	K	0.18	31	95.4	6.1	96.3	21.4	47.6
16	3	L	0.35	50	97.8	5	97.3		
17	4	G	0.35	66	96.9	5.1	95.2		
C4	C1	G	0.35	41	92.5	4.3	---		
C5	C2	G	0.35	65	96.8	6.1	96.3		
C6	C3	G	0.35	39	94.2	3.5	94.2		
C7	C3	H	0.35	34	94.0	4.1			
C8	C3	I	0.35	15	95.9	3.9	93.8		
C9	C3	J	0.35	19	90.8	4.2	93.1		
C10	C3	K	0.35	28	95.7	4.3	95.9		

G= Trifluoropropylmethyldimethoxysilane

H= Octylmethyldimethoxysilane

I= Methyl trimethoxysilane


J= Tetramethoxysilane

K= Tetraethoxysilane

L= Cyclohexylmethyl dimethoxysilane

CLAIMS

1. Catalyst components for the polymerization of olefins $\text{CH}_2=\text{CHR}$ in which $\text{CH}_2=\text{CHR}$ in which R is hydrogen or a hydrocarbyl radical with 1-12 carbon atoms, comprising Mg, Ti, halogen and at least two electron donor compounds, said catalyst component being characterized by the fact that at least one of the electron donor compounds, which is present in an amount from 15 to 50% by mol with respect to the total amount of donors, is selected from esters of succinic acids which are not extractable, under the conditions described above, for more than 20% by mol and at least another electron donor compound which is extractable, under the same conditions, for more than 30% by mol.
2. Catalyst components according to claim 1 characterized by the fact that the amount of non-extractable succinate is between 20 and 40% by mol based on the total amount of electron donor compounds present on the catalyst.
3. Catalyst components according to claim 1 characterized by the fact that the non-extractable succinate is extractable for not more than 15% by mol.
4. Catalyst components according to claim 1 characterized by the fact that the extractable electron donor compound is extractable for more than 40% by mol.
5. Catalyst components according to claim 1 characterized by the fact that the non-extractable succinates are those of formula (I)



in which the radicals R_1 and R_2 , equal to, or different from, each other are a $\text{C}_1\text{-C}_{20}$ linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms; and the radicals R_3 and R_4 equal to, or different from, each other, are $\text{C}_1\text{-C}_{20}$ alkyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms with the proviso that at least one of them is a branched alkyl; said compounds being, with respect to the two asymmetric carbon atoms identified in the structure of formula (I), stereoisomers

- of the type (S,R) or (R,S) that are present in pure forms or in mixtures.
6. Catalyst components according to claim 1 in which the extractable electron donor compound is selected from esters of phthalic acids.
 7. Catalyst components according to claim 1 in which the extractable electron donor compound is selected from alkyl esters of phthalic acids.
 8. Catalyst components according to claim 1 in which the extractable electron donor compound is selected from the (S,S), (R,R) or *meso* forms of the succinates of formula (I).
 9. Catalyst components according to claim 8 further comprising alkyl esters of phthalic acids as extractable donors.
 10. Catalyst components according to claim 1 in which mixture of succinates of claim 5 are used as non-extractable donors.
 11. Catalyst components according to any of the claims 1-10 comprising a titanium compound having at least one Ti-halogen bond supported on a Mg dichloride.
 12. Catalyst components according to claim 11 having a surface area (by B.E.T. method) between 20 and 500 m²/g and a total porosity (by B.E.T. method) higher than 0.2 cm³/g.
 13. Catalyst for the polymerization of olefins comprising
 - (i) the solid catalyst component according to claim 1,
 - (ii) an organo-metal compound and
 - (iii) an external electron donor compound.
 14. Catalyst according to claim 13 in which the organo-metal compound is an alkyl-Al compound.
 15. Catalyst according to claim 13 in which the external electron compound is selected from silanes of formula R⁵_aR⁶_bSi(OR⁷)_c, where a and b are integers from 0 to 2, c is an integer from 1 to 4 and the sum (a+b+c) is 4; R⁵, R⁶, and R⁷, are alkyl, alkylen, cycloalkyl or aryl radicals with 1-18 carbon atoms optionally containing heteroatoms.
 16. Catalyst according to claim 15 in which the silane is selected from those having a low stereoregulating ability.
 17. Catalyst according to claim 15 in which the silane is selected from those in which R⁵ is methyl, R⁶ is a C1-C15 linear alkyl and R⁷ is a linear C1-C4 alkyl.
 18. Catalyst according to claim 15 in which the silane is selected from those in which R⁵ is a trifluoropropyl group, optionally substituted, R⁶ is a C1-C6 linear alkyl or a piperidinyl

group, optionally substituted, and R⁷ is a linear C1-C4 alkyl.

19. Catalyst according to claim 15 in which the silane is selected from those in which c is 3 or 4.
20. Process for the preparation of propylene polymers characterized by the fact that the polymerization is carried out in the presence of a catalyst according to any of the claims 14-19.
21. A propylene polymer having the following characteristics:
 - a stereoblock content of 18% or higher measured by the TREF method;
 - a Polydispersity Index of at least 5 and
 - a percentage of pentads (mmmm), measured by NMR, lower than or equal to 97.
22. Propylene polymer according to claim 20 having a stereoblock content higher than 20%.
23. Propylene polymer according to claim 20 or 21 having a P.I. higher than 5.3
24. Propylene polymer according to any of claim 21-23 having a percentage of pentads lower than 96.5.
25. Propylene polymer according to any of claim 21-24 showing, at the TREF analysis, a fraction eluted at a temperature ranging from 110° and 114°C which accounts for more than 25% of the total weight of the polymer.

INTERNATIONAL SEARCH REPORT

In International Application No
PCT/EP 01/11048

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08F4/651 C08F4/654 C08F10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 522 930 A (ALBIZZATI ENRICO ET AL) 11 June 1985 (1985-06-11)	1-4, 11-16,20
Y	column 7, line 20 -column 8, line 17 column 8; examples 5,6; table 1	18,19
X	EP 0 658 577 A (HIMONT INC) 21 June 1995 (1995-06-21)	21
Y	claims 1,2 examples 1,7	18,19
	--- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

19 February 2002

Date of mailing of the international search report

28/02/2002

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Fischer, B

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 01/11048

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 00 63261 A (BALBONTIN GIULIO ; MORINI GIAMPIERO (IT); MONTELL TECHNOLOGY COMPAN) 26 October 2000 (2000-10-26) page 19 examples 10,11,30; table 1 examples 31,33,34 example 40 examples 43,45 claims 1,6,8,9,10,11,12,15,16,19,25,37,38-40	1,3-9, 11-15, 18,20
X	EP 0 982 328 A (TOKUYAMA CORP) 1 March 2000 (2000-03-01) comparative example 1; Table 1	21,22
X	KONG X ET AL: "Temperature rising elution fractionation of polypropylene produced by heterogeneous ziegler-natta catalysts" EUROPEAN POLYMER JOURNAL, PERGAMON PRESS LTD. OXFORD, GB, vol. 34, no. 3-4, 1 March 1998 (1998-03-01), pages 431-434, XP004137942 ISSN: 0014-3057 page 433; tables 1,2	21,22
A	SOBOTA, PIOTR ET AL: "Ionization of TiCl ₄ and MgCl ₂ during the Formation of a High-Activity.alpha.-Olefin Polymerization Catalyst. Crystal Structures of 'cis-{C ₂ H ₄ (CO ₂ Et) ₂ } ₂ Cl ₂ Ti!'SbCl ₆ !2.cntdot. CH ₂ Cl ₂ and 'Mg{C ₂ H ₄ (CO ₂ Et) ₂ } ₃ !'MgCl ₄ !.cntdot.2CH ₂ Cl ₂ " INORG. CHEM. (1996), 35(7), 1778-81 , XP001061301 page 1780, column 2	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/11048

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4522930	A	11-06-1985	IT 1190683 B	24-02-1988
			AT 27286 T	15-06-1987
			AU 561820 B2	21-05-1987
			AU 1128583 A	18-08-1983
			BR 8300673 A	08-11-1983
			CA 1211099 A1	09-09-1986
			DE 3371638 D1	25-06-1987
			EP 0086473 A2	24-08-1983
			ES 519706 D0	16-03-1984
			ES 8403142 A1	01-06-1984
			GR 77923 A1	25-09-1984
			IN 161721 A1	23-01-1988
			JP 8016124 B	21-02-1996
			JP 58145707 A	30-08-1983
			JP 2693707 B2	24-12-1997
			JP 6192316 A	12-07-1994
			MX 163288 A	09-04-1992
			PT 76225 A ,B	01-03-1983
			US 4904628 A	27-02-1990
EP 0658577	A	21-06-1995	AT 155498 T	15-08-1997
			AU 686681 B2	12-02-1998
			AU 8047194 A	22-06-1995
			BR 9405120 A	22-08-1995
			CA 2138223 A1	17-06-1995
			CN 1106824 A	16-08-1995
			DE 69404270 D1	21-08-1997
			DE 69404270 T2	15-01-1998
			DK 658577 T3	27-10-1997
			EP 0658577 A2	21-06-1995
			ES 2107109 T3	16-11-1997
			JP 7252312 A	03-10-1995
			RU 2138514 C1	27-09-1999
WO 0063261	A	26-10-2000	AU 4548600 A	02-11-2000
			BR 0006095 A	20-03-2001
			CN 1313869 T	19-09-2001
			WO 0063261 A1	26-10-2000
			EP 1088009 A1	04-04-2001
			HU 0103083 A2	28-11-2001
			NO 20006388 A	29-01-2001
EP 0982328	A	01-03-2000	EP 0982328 A1	01-03-2000
			JP 2000239462 A	05-09-2000
			US 6268063 B1	31-07-2001